

Test Report**Report Number: 160510008SHF-BP-1****Applicant Name:** MexyTech Co.,Ltd**Report Date:** May 17, 2016**Applicant Address:** No.2-8 Building B, Torch
Innovation Park, Jihua 2 Road,
Foshan City, Guangdong**Attn:** Tiger Feng**Sample Description:**

Product: ECOLEGNO COMPOSITE WOOD
Model: DECKING AND WALL CLADDING
Sample Quantity: 24 pieces
Sample ID: S160426011SHF-001~024
Date Received: 2016/4/25
Date Test Conducted: 2016/5/5

Tests Conducted:

As requested by the applicant, for details refer to attached pages(s).

Conclusion:

For details refer to attached page(s).
The conclusions of this test report may not be used as part of the requirements for Intertek product certification. Authority to Mark must be issued for a product to become certified.

I. INTRODUCTION

This report describes the results of the ASTM E84-15b TEST FOR SURFACE BURNING CHARACTERISTICS OF BUILDING MATERIALS a method for determining the comparative surface burning behavior of building materials. This test is applicable to exposed surfaces, such as ceilings or walls, provided that the material or assembly of materials, by its own structural quality or the manner in which it is tested and intended for use, is capable of supporting itself in position or being supported during the test period.

The purpose of the method is to determine the relative burning behavior of the material by observing the flame spread along the specimen. Flame spread and smoke density developed are reported, however, there is not necessarily a relationship between these two measurements.

“The use of supporting materials on the underside of the test specimen may lower the flame spread index from that which might be obtained if the specimen could be tested without such support... This method may not be appropriate for obtaining comparative surface burning behavior of some cellular plastic materials... Testing of materials that melt, drip, or delaminate to such a degree that the continuity of the flame front is destroyed, results in low flame spread indices that do not relate directly to indices obtained by testing materials that remain in place.”

This test method is also published under the following designations:

NFPA 255

UL 723

UBC 8-1

This standard should be used to measure and describe the properties of materials, products, or assemblies in response to heat and flame under controlled laboratory conditions and should not be used to describe or appraise the fire hazard or fire risk of materials, products, or assemblies under actual fire conditions. However, results of this test may be used as elements of a fire risk assessment which takes into account all of the factors which are pertinent to an assessment of the fire hazard of a particular end use.

II. PURPOSE

The ASTM E84 (25 foot tunnel) test method is intended to compare the surface flame spread and smoke developed measurements to those obtained from tests of fiber cement board and select grade red oak flooring. The test specimen surface (18 inches wide and 24 feet long) is exposed to a flaming fire exposure during the 10 minute test duration, while flame spread over its surface and density of the resulting smoke are measured and recorded. Test results are presented as the computed comparisons to the standard calibration materials.

The furnace is considered under calibration when a 10 minute test of red oak decking will pass flame out the end of the tunnel in five minutes, 30 seconds, plus or minus 15 seconds. The fiber cement board which complies with Annex A3 of the ASTM E 84 standard forms the zero point for both flame spread and smoke developed indexes, while the red oak flooring smoke developed index is set as 100.

III. TEST PROCEDURE

The tests were conducted in accordance with the procedures outlined in the ASTM E84-15b. The specimens are placed directly on the tunnel ledges. As required by the standard, one or more layers of 0.25 inch thick reinforced concrete board are placed on top of the test sample between the sample and the tunnel lid. After the test, the samples are removed from the tunnel, examined and disposed of.

IV. DESCRIPTION OF TEST SPECIMENS

Date Received: 4/25/2016

Date placed in the conditioning room: 4/26/2016

Conditioning (73°F & 50% R.H.): 9 days

Specimen Width (in): 22.04

Specimen Length (ft): 23.62

Specimen Thickness (in): 0.87

Total Specimen Weight (lbs): 221.28

Specimen Description:

The specimen was described by the client as: "ECOLEGNO COMPOSITE WOOD, model of DECKING AND WALL CLADDING".

The 23.62-ft. long test specimen consisted of twenty-four sections of 3.94-ft. long x 5.51-in. wide x 0.87-in. thick "ECOLEGNO COMPOSITE WOOD, model of DECKING AND WALL CLADDING". Four sections were placed side by side to get a 22.04-in. width.

Test Report**Report Number: 160510008SHF-BP-1****V. TEST RESULTS**

The test results, computed on the basis of observed flame front advance and electronic smoke density measurements are presented in the following table.

Test Specimen	Flame Spread Index	Smoke Developed Index
"ECOLEGNO COMPOSITE WOOD, model of DECKING AND WALL CLADDING"	10	5

The data sheets are included in attached page. These sheets are actual print-outs of the computerized data system which monitors the tunnel furnace, and contain all calibration and specimen data needed to calculate the test results.

VI. OBSERVATIONS

During the test, the specimen was observed to behave in the following manner.

Time (min:sec)	Observations
0:00	The test burners were turned on.
3:04	Transient ignition was observed.
4:05	Steady ignition was observed.
10:00	The test burners were shut off.
After the burners were turned off, a 60+ seconds after flame was observed.	

After the test, the specimen was observed to be damaged as follows:

Distance (FEET)	Damage Descriptions
0-7	The specimen was charred and sagging.
7-24	The specimen was discolored and sagging.

Mounting Method:

The specimen was supported with 0.25-in. diameter metal rods that were spaced approximately every two feet and 20-gage, 2-in. hexagonal galvanized steel netting.

The smooth side was exposed to the flames.

Mounting Method pic



Test Report

Report Number: 160510008SHF-BP-1

DATA SHEET:

Test Method Lab ID Project #
 ASTM E84 Intertek Fire Laboratory 160426011

Date
 05 May 2016 Time (Test Start) 1:42 PM Test No. 3

Specimen ID
 ECOLEGNO COMPOSITE WOOD


Specimen Description
 DECKING

Mounting Procedure
 Support with rod and steel netting

Fuel (CF) 43 RO Smk Area 54.7 Smoke Area (%A min) 3.99

FS Area (ft-min) 22.8 Maximum FS 4.60

MAX FS Time (min) 8.99 Max Temp 587.9



Raw SD 7.3 Final FSI 10 Final SD 5

Time to 980F (min) 0.00

Appendix A: Sample received photo



Approved by:

Name: Sun Sun
Title: Approver

Name: Harrison Li
Title: Reviewer

Name: Timothy Li
Title: Project Engineer

The End of Report

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.